

**Manufacturer:**

Europanel Sp. z o.o., 5/81 Inflancka Street, 00-189 Warszawa, Poland

Production plant: 35 Latkowo, 88-100 Inowrocław, Poland

12

Certificate of Conformity – Declaration of Performance

ref. no. TS200PIR/EP/L,M,R,P/1/2023/ENG

Product name (ID code): PolTherma TS 200 PIR L, M, R, P

Use: External walls, internal walls, ceilings

Product description: Metal faced insulating panel for use in buildings

European standard: EN 14509:2013-12 „Self-supporting double skin metal faced insulating panels – Factory made products – Specifications “

System of conformity: fire performance: System 3, other performances: System 4

ID of the notified bodies: ITB Warszawa, notification no. 1488; FIRES s.r.o. Batizovce, notification no. NO 1396
CERTBUD Sp. z o.o. Warszawa, notification no NB 2310

Declared performance parameters of the product:

Facings: Steel metal plate galvanized according to EN 10346, thickness range 0,4 to 0,7 mm in tolerances according to EN 10143. Protective coats according to EN 10169. Colours according to RAL Classic.

Profiling of external facing: L (linear), M (micro profiled), R (rabbet), P (plain)

Profiling of internal facing: L (linear), M (micro profiled), R (rabbet), P (plain)

Thermal insulation: rigid PIR foam, density 38 +/- 3,8 kg/m³

Thermal transmittance $U_{d,s}$: 0,11 W/m²K

Declared thermal conductivity λ_D : 0,022 W/mK

Weight: 15,6 kg/m² (at mean density)

Fire parameters:

- reaction to fire of the core (ignition test according to EN ISO 11925-2):

class E

- reaction to fire of the product (classification according to EN 13501-1):

B-s1,d0

- fire resistance of the partition made out of the product (classification according to EN 13501-2):

EI 30 (i ↔ o); EW 30 (o ↔ i) horizontal layout, max span 7,5 m

EI 15 (i ↔ o); E 30 (o ↔ i) horizontal layout, max span 7,5 m

Durability: Fulfils, for all colours

Dimensional tolerances: Fulfils

Tightness:

- water permeability: class A (1 200 Pa)
- air permeability: $\leq 0,10 \text{ m}^3/\text{h}/\text{m}^2$
- steam permeability: fulfils, impermeable

Acoustic parameters:

- airborne sound insulation: R_w 26 (-3, -4) dB
- sound absorption: $\alpha_w = 0,15$

Shear strength f_{cv} : 0,093 MPa; **Shear modulus (core) G_c :** 1,78 MPa

Creep coefficient ϕ_t : $t=2\ 000\text{h}$: 2,78; $t=100\ 000\text{h}$: 3,55

Compressive strength (core) f_{cc} : 0,10 MPa; **Compressive E-modulus (core) E_{cc} :** 2,7 MPa

Tensile strength f_{ct} : 0,06 MPa; **Tensile E-modulus of the core (+20 °C) E_{ct} :** 3,8 MPa

Bending resistance in span M_u ; S280; 0,5 mm (for 0,4 mm in brackets):

- positive bending, external, ambient temperature: 11,73 kNm/m
- positive bending, external, elevated temperature: 10,49 kNm/m
- negative bending, internal, ambient temperature: 10,46 (8,19) kNm/m
- negative bending, internal, elevated temperature: 9,35 (7,32) kNm/m

Bending resistance at an internal support M_u ; S280; 0,5 mm (for 0,4 mm in brackets):

- negative bending, ambient temperature: 10,68 kNm/m
- negative bending, elevated temperature: 9,55 kNm/m
- positive bending, ambient temperature: 8,59 (6,73) kNm/m
- positive bending, elevated temperature: 7,68 (6,02) kNm/m

Wrinkling stress, external facing σ_w ; S280

- in span, ambient temperature: 127,79 MPa
- in span, elevated temperature: 114,28 MPa
- at central support, ambient temperature: 116,37 MPa
- at central support, elevated temperature: 104,07 MPa

Wrinkling stress, internal facing σ_w ; S280

- in span, ambient temperature: 113,96 MPa
- in span, elevated temperature: 101,91 MPa
- at central support, ambient temperature: 93,63 MPa
- at central support, elevated temperature: 83,74 MPa

This document is released at the sole responsibility of the Producer

EUROPANELS

Spółka z o.o.

00-189 Warszawa, ul. Inflancka 5 lok. 81
NIP 525-246-35-41

WARSZAWA, April 25th 2023

Place and date

Prokurent

Janusz Szczepański

Web site with declaration for download: www.europanels.pl